

AMENDMENTS TO THE CLAIMS

This listing of claims replaces all prior versions of claims in the application.

1. (Currently amended): A toner comprising a colored resin particle and an external additive,
wherein said external additive comprises a silica fine particle (A) having
a Dv50/Dv10 of 1.8 or more, in which Dv10 represents a particle diameter at which a
volume cumulative total from small particle diameter side is 10% and Dv50 represents a particle
diameter at which the mentioned volume cumulative total is 50%,
a volume average particle diameter in the range from 0.1 to 1.0 μ m, [[and]]
a sphericity in the range from 1 to 1.3, and
wherein the silica fine particle (A) has a Dv50/Dv10 of 2 or more.
2. (Cancelled).
3. (Original): The toner according to claim 1,
wherein the silica fine particle (A) has an volume average particle diameter in the range
from 0.1 to 0.5 μ m.
4. (Original): The toner according to claim 1,
wherein the silica fine particle (A) has an appearance bulk density in the range from 50 to
250g/l.

5. (Original): The toner according to claim 1,

wherein the silica fine particle (A) has an appearance bulk density in the range from 80 to 200g/l.

6. (Original): The toner according to claim 1,

wherein the silica fine particle (A) is produced by a melting method.

7. (Original): The toner according to claim 1,

wherein the external additive further comprises a silica fine particle (B) having a volume average particle diameter in the range from 5 to 80nm.

8. (Original): The toner according to claim 1,

wherein the external additive further comprises a silica fine particle (B) having a volume average particle diameter in the range from 7 to 30nm.

9. (Original): The toner according to claim 8,

wherein the external additive further comprises a conductive inorganic fine particle (C) having a number average particle diameter in the range from 0.01 to 2 μ m.

10. (Original): The toner according to claim 8,

wherein the external additive further comprises a conductive inorganic fine particle having a number average particle diameter in the range from 0.03 to 1 μ m.

11. (Original): The toner according to claim 1,

wherein the colored resin particle has a volume average particle diameter D_v in the range from 3 to 15 μ m.

12. (Original): The toner according to claim 1,

wherein the colored resin particle has a ratio (D_v/D_p), of a volume average particle diameter (D_v) to a number average particle diameter (D_p), in the range from 1.0 to 1.3.

13. (Original): The toner according to claim 1,

wherein the colored resin particle has a sphericity from 1.0 to 1.3.

14. (Original): The toner according to claim 1 further comprises a parting agent.

15. (Original): The toner according to claim 14,

wherein the parting agent is a synthetic wax or a polyfunctional ester compound.

16. (Original): The toner according to claim 1 further comprises a charge control agent.

Application No.: 10/570,151
Art Unit: 1795

Amendment under 37 CFR §1.111
Attorney Docket No.: 071850

17. (Original): The toner according to claim 16,

wherein the charge control agent is a charge control resin having a weight average molecular weight in the range from 2,000 to 50,000.